



ITALGRANITI

LUX EXPERIENCE WALL

SPECIFICATION WHITE BODY WALL TILES



MATERIAL

White body wall tiles.

Classificate nel GROUP BIII GL CON Ev > 10%.

This material complies with all the requirements of UNI EN 14411 ISO 13006 APP. L

Thanks to its passion for the most refined marbles, Italgraniti combines gleaming marble-like effects with textured three-dimensional modules, creating the finest ingredients for settings that reflect versatility and glam style.

COLOR	SIZES	SURFACE	THICKNESS
 STATUARIETTO	RECTIFIED 32x96,2 (12 ^{1/2"} x 37 ^{1/8"})	SHINY	11,5 MM
 PIETRA GREY			

PRODUCTION PROCESS

Monoporosa tiles obtained by dry pressing a compact white body mix consisting of choice clays. The surface is glossy glazed. The colours are obtained using high-purity colorant oxides. The decoration is obtained using the innovative digital technology which provides a peerless appearance, re-creating the countless vein patterns of marble with high definition and extremely precise details. The tiles are fired in single-layer roller kilns at a temperature around 1,140°C.

Size

Finishes

Color Type



ITALGRANITI

LUX EXPERIENCE WALL











WALL

TECHNICAL TABLE WHITE BODY WALL TILES

CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX L GROUP BIII GL CON Ev > 10%

PHYSICAL PROPERTIES	TESTING METHOD	REFERENCE STANDARD	PRODUCT VALUES		
 Sizes	EN ISO 10545-2	N ≥ 15 cm			
		(%)	(mm)		
		Length and width	±0.6	±2.0	
		Thickness	±5.0	±0.5	
		Linearity	±0.5	±1.5	
		Wedging	±0.5	±2.0	Rectified
		Warpage	±0.5	±2.0	Conforming
		Centre curvature	±0.5	±2.0	
		Edge curvature	±0.5	±2.0	
		Warpage	±0.5	±2.0	
Surface quality		95% of tiles with no visible flaws			
 Water absorption %	EN ISO 10545-3	Eb >10%	Conforming		
 Modulus of rupture Breakage resistance	EN ISO 10545-4	sp. > = 7,5 mm: min 12 N/mm ²	Conforming		
		sp. > = 7,5 mm: min 600 N	Conforming		
 Thermal expansion coefficient	EN ISO 10545-8	Stated value	7 MK ⁻¹		
 Thermal shock resistance	EN ISO 10545-9	* Testing method available	Resistant		
 Glaze crazing resistance	EN ISO 10545-11	* Testing method available	* Resistant		
 Resistance to low concentrations of acids and alkali Resistance to domestic chemicals and additives for swimming pools	EN ISO 10545-13	Stated value	Resistant		
		GB min.	Conforming		
 Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Classe 3 min.	Conforming		